

# CERALOX

## MAGNESIUM ALUMINATE SPINEL



SASOL

### Typical chemical properties

Product	Primary impurities (ppm)								
	Na	Si	Fe	Ca	Ti	Cr	Ni	Zn	Zr
AHPA – Spinel	10	15	5	5	2	2	2	2	3
AHPA – Spinel – AF	10	15	5	5	2	2	2	2	3
APA – MG28 – AF	30	70	100	5	10	10	5	25	3

### Typical physical properties

Product	AHPA – Spinel	AHPA – Spinel – AF	APA – MG28 – AF
d90 particle size ( $\mu\text{m}$ )	60	5,0	7,0
d50 particle size ( $\mu\text{m}$ )	35	1,2	3,0
Surface area ( $\text{m}^2 / \text{g}$ )	20	25	17
Powder form	Unmilled powder	Milled powder	Milled powder
Primary crystalline phase	Spinel - $\text{Mg Al}_2\text{O}_4$	Spinel - $\text{Mg Al}_2\text{O}_4$	Spinel - $\text{Mg Al}_2\text{O}_4$
$\text{Al}_2\text{O}_3$ : $\text{MgO}$ molar ratio	1,01:1	1,01:1	1:1

### Methodology

- Chemical analysis: Leeman Labs Inductively Coupled Argon Plasma
- Particle size distribution: Horiba® Laser Diffraction
- Surface area: B.E.T. Micromeritics® Gemini
- Crystalline phase: X-ray Powder Diffraction

### CONTACT INFORMATION

For technical information or samples please contact: [Ceraloxcs@us.sasol.com](mailto:Ceraloxcs@us.sasol.com)

#### Sasol Chemicals North America LLC - CERALOX

7800 South Kolb Road - Tucson, Arizona 85756

Telephone 520-294-5201

Facsimile 520-294-5208

Toll Free: 800-874-6688 (in U.S.)

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including any existing third party patent rights. In particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other companies is neither a recommendation, nor is it intended to suggest that similar products could not be used. All our business transactions shall be governed exclusively by our general sales conditions.

## CONTACT INFORMATION

For technical information or samples please contact: [MWL@de.sasol.com](mailto:MWL@de.sasol.com)

### **Sasol North America, Inc. - Ceralox Division**

7800 South Kolb Road - Tucson, Arizona 85756

Telephone 520-294-5201

Facsimile 520-294-5208

Toll Free: 800-874-6688 (in U.S.)

This information is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including any existing third party patent rights. In particular, no guarantee of properties in the legal sense is implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not exempted from the obligation to conduct careful inspection and testing of incoming goods. Reference to trade names used by other companies is neither a recommendation, nor is it intended to suggest that similar products could not be used. All our business transactions shall be governed exclusively by our general sales conditions.