

product data sheet

Hydrowax 652

Code 1919 Revision 4 25 July 2015

Properties	Test method	Units	Specification	Typical values
pH	Sasol Wax 019		9 max	8.5
Viscosity at 25 °C (6mm DIN Beaker)	Sasol Wax 1012	seconds	-	5.5
Solids content	Sasol Wax 1008	mass %	44 – 48	46
Shear stability (hand)	Sasol Wax 1010		Pass	Pass
Dilution stability	Sasol Wax 1013		Pass	Pass
Density at 20 °C	Sasol Wax 1001	kg/l	-	0.95

Compliance

F&DA: This product complies with the requirements of 21 Code of Federal Regulations: 175.105(Adhesives), 175.250 (Paraffin, synthetic), 175.300 (Resinous & Polymeric coatings), 175.320 (Resinous & Polymeric coatings for Film), 176.170 (Components of Paper & Paperboard, Wet), 176.180 (Components of Paper & Paperboard, Dry), 177.1200 (Cellophane), 177.1390 (Laminate Structures).

BGA: This product complies with BGA requirement XXV, Part C, (Synthetische Hartparaffine).

Packaging

Hydrowax 652 is supplied as a liquid in bulk and 180 kg plastic barrels.

Note

To obtain the best performance from the product, we recommend use within 6 Months from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

Notice This product information is indicative and does not include any guarantee

Sasol Chemicals a division of Sasol South Africa (Pty) Ltd.
ISO 9001/ISO 14001