

product data sheet

Sasolwax B52

Code 1985 Revision 13 16 November 2020

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	98 - 106	102
Penetration at 25°C	ASTM D 1321	0.1 mm	2 max	1
Acid value	ASTM 1386/7	mg KOH/g	2 – 4	3
Particle size < 106 micron > 2000 micron	ASTM D 185	mass %	10 max 2 max	5 0
Appearance (Visual)	Sasol 1074	-	Free from grey matter or any contamination	Pass

Packaging

Sasolwax B52 is supplied in coarse powder packed in 20kg paper and/or 20kg and jumbo polyethylene bags.

Note

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C

Notice This product information is indicative and does not include any guarantee

Sasol Chemicals a division of Sasol South Africa (Pty) Ltd.
ISO 9001/ISO 14001