

product data sheet

Hydrowax 112

Code 1938 Revision 6 25 July 2015

Properties	Test method	Units	Specification	Typical values
Solids content	Sasol Wax 1008	mass %	48 – 52	50
Oil Content (calculated)	Sasol Wax 024	mass %	-	9
pH	Sasol Wax 019		7.5 – 10.0	9.0
Viscosity at 25 °C (6mm DIN Beaker)	Sasol Wax 1012	seconds	-	10.0
Shear stability (hand)	Sasol Wax 1010		Pass	Pass
Shear stability (pump)	Sasol Wax 1009	mass %	1.2 max	0.8
Density at 20 °C	Sasol Wax 1001	kg/l	-	0.95
Dilution stability	Sasol Wax 1013		Pass	Pass
Compatibility with:				
- urea formaldehyde				Good
- phenol formaldehyde				Good

Packaging

Hydrowax 112 is supplied as a liquid in bulk and 180 kg plastic barrels.

Note

To obtain the best performance from the product, we recommend use within 1 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

Notice **This product information is indicative and does not include any guarantee**