

## product data sheet

### MERKUR 140

Code 1705      Revision 5      06 September 2018

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D938	°C	56 – 62	58
Drop point	Sasol Wax 1002	°C	58.0 – 68.0	62.0
Needle penetration at 25°C	ASTM D1321	0.1mm	35 - 55	45
Colour Lovibond	Sasol Wax 1019	y	1.5 max	1.2
Oil content	ASTM D721	Mass%	3 - 7	5

#### Packaging

MERKUR 140 is supplied as slabs in 25kg boxes.

#### Note

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

#### Notice

**This product information is indicative and does not include any guarantee**