

product data sheet

SASOBIT

Code 1596 Revision 16 06 August 2018

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	100 - 110	101
Penetration at 25°C	ASTM D 1321	0.1 mm	0 - 2	<1
Penetration at 65°C	ASTM D 1321	0.1 mm	0 - 13	11
Brookfield viscosity at 135°C	Sasol 1010	сР	10 – 15	12
Visual colour compliance	Visual	-	Pass/Fail	Pass

Compliance

F&DA:

This product complies with the requirements of 21 Code of Federal Regulations: Parts 175.105(Adhesives), 177.1390 (Laminate Structures).

Note

To obtain the best performance from the product, we recommend use within 10 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

Notice This product information is indicative and does not include any guarantee