

## product data sheet

### Sasolwax C

Code 1502    Revision 8    07 April 2016

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	26 - 32	27
Oil content	ASTM D 721	mass %	22 max	14.0
Flash point	ASTM D93	°C	120 min	150

#### Packaging

Sasolwax C is supplied in liquid bulk and 153kg open top steel drums

#### Note

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

**Notice**      **This product information is indicative and does not include any guarantee**