

product data sheet

Sasolwax B52

Code 1985 Revision 12 15 March 2017

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D 938	°C	98 - 106	102
Penetration at 25°C	ASTM D 1321	0.1 mm	2 max	1
Acid value	ASTM 1386/7	mg KOH/g	2 – 4	3
Particle size < 106 micron > 2000 micron	ASTM D 185	mass %	10 max 2 max	5 0
Appearance (Visual)	Sasol 1074	-	Free from grey matter or any contamination	Pass

Packaging

Sasolwax B52 is supplied in coarse powder packed in 20kg paper bags and jumbo bags

Note

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C

Notice This product information is indicative and does not include any guarantee

Sasol Chemicals a division of Sasol South Africa (Pty) Ltd.
ISO 9001/ISO 14001