

## product data sheet

### MERKUR 108

Code 7557    Revision 5    06 September 2018

Properties	Test method	Units	Specification	Typical values
Congealing point	ASTM D938	°C	59 – 65	62
Drop point	Sasol Wax 1002	°C	-	72
Needle Penetration at 25°C	ASTM D1321	0.1mm	25-45	38
Colour Lovibond	Sasol Wax 1019	y	1.5 max	0.6
Colour Lovibond	Sasol Wax 1019	r	0.5 max	0.4

#### Packaging

MERKUR 108 is supplied as slabs in 25kg boxes.

#### Note

To obtain the best performance from the product, we recommend use within 5 years from sample date on the Certificate of Analysis. Product should be stored under standard warehousing conditions, at least in a clean dry place, in its original packing at a temperature not exceeding 35°C.

**Notice**                      **This product information is indicative and does not include any guarantee**