

PRODUCT DATA SHEET



hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE

Linear Low Density Polyethylene

HF1832X

Technical support:

Sasol Chemicals
North America LLC
12120 Wickchester Lane
Houston, TX 77079

Email:

PolymersTechnical@us.sasol.com

Sales office:

Sasol Chemicals
North America LLC
12120 Wickchester Lane
Houston, TX 77079
Telephone: (281) 588 3000
Email:
PolymersSales@us.sasol.com

Date of issue: February 21, 2019

www.sasol.com

Melt Index: 3.2 g/10min

Density: 0.918 g/cm³

Features

- LLDPE Hexene copolymer
- Excellent tensile properties, puncture and toughness
- Outstanding unitization holding force
- Superior drawability

Applications

- Cast stretch film for pallet unitization for cling wrapping

Additives

- Antioxidant
- TNPP Free

Typical properties (not to be construed as specifications)		Value (English)	Value (SI)	Method
Resin Properties	Melt Index (190°C/2.16kg)	3.2 g/10min	3.2 g/10min	ASTM D1238
	Density	0.918 g/cm ³	0.918 g/cm ³	ASTM D792
	Base Density ⁽¹⁾	0.918 g/cm ³	0.918 g/cm ³	Sasol Method
Film Properties	Tensile strength at yield MD	1450 psi	10.0 MPa	ASTM D882
	Tensile strength at yield TD	1305 psi	9.0 MPa	ASTM D882
	Tensile Elongation at break MD	750%	750%	ASTM D882
	Tensile Elongation at break TD	830%	830%	ASTM D882
	1% Secant Modulus MD	24000 psi	165 MPa	ASTM D882
	1% Secant Modulus TD	25000 psi	172 MPa	ASTM D882
	Elmendorf Tear Strength MD	370 g	370 g	ASTM D1922
	Elmendorf Tear Strength TD	500 g	500 g	ASTM D1922
	Dart Drop Impact Strength	120 g	120 g	ASTM D1709A
	Haze	2.5%	2.5%	ASTM D1003
	Gloss (45°)	90%	90%	ASTM D2457

(1) Base density is calculated assuming that the product doesn't contain any antiblock additive.

The above values were measured on a 1.0 mil (25.4 µm) film produced on a cast film line with a melt temperature of 510 °F (266 °C)

hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE hLLDPE

Processing

HF1832X is formulated for cast monolayer and coextruded film, and has good thermal stability at elevated temperatures.

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses are suggested as a minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapours. Please consult the material safety data sheet (SDS) for more detailed information.

Storage

As ultraviolet light may cause a change in the material, all resins should be protected from direct sunlight during storage. If stored in cool (<25°C), dry area with low ambient light levels, polyolefin resins are expected to maintain their original material and processing properties for at least 12 months.

Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources. In burning, polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and water mist preferred. In enclosed areas, fire fighters should be provided with self contained breathing apparatus.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles that are contained in all polyethylene resins. The fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. be equipped with adequate filters
2. is operated and maintained in such a manner to ensure no leaks develop
3. that adequate grounding exists at all times

It is further recommended that good housekeeping is practiced throughout the facility.

This publication contains information provided in good faith and is indicative, based on Sasol's current knowledge on the subject. No guarantee or warranty is intended or implied. We reserve the right to make changes as a result of technological progress or development. Any information, including suggestions for use of products, should not preclude experimental testing and verification, to ensure the suitability of a product for each specific application. Users must also abide by local and international laws and obtain all necessary permits when required to do so. Prior to handling a hazardous product, consult its safety data sheet. In case of questions or queries, please contact Sasol through our customer service channels. All products purchased or supplied by Sasol Chemicals are subject to the terms and conditions set out in the contract, order confirmation and/or bill of lading. All data herein not to be construed as specifications.